Toward the control of thickness and uniformity in the coating of TiO₂-P25 on glass

Jihène Soufi, Miriam Pastor-Franco, Shuzhen Zhou, Reddad Hardala, Floriane Houillon, Valérie Meille, Dominique Richard

► To cite this version:

Jihène Soufi, Miriam Pastor-Franco, Shuzhen Zhou, Reddad Hardala, Floriane Houillon, et al.. Toward the control of thickness and uniformity in the coating of TiO₂-P25 on glass. *Particulate Science and Technology*, 2015, 34 (2), pp.229 - 234. 10.1080/02726351.2015.1068898 . hal-01925602

HAL Id: hal-01925602

<https://univ-lyon1.hal.science/hal-01925602>

Submitted on 9 Apr 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Towards the control of thickness and uniformity in the coating of TiO₂-P25 on glass

Jihène Soufi, Miriam Pastor-Franco, Shuzhen Zhou, Reddad Hardala,

Floriane Houillon, Valérie Meille*, Dominique Richard

Université de Lyon, Institut de Chimie de Lyon, Laboratoire de Génie des Procédés Catalytiques, CNRS, CPE Lyon,
43 bd du 11 novembre 1918, BP 82077, 69616 Villeurbanne cedex, France

* Corresponding author, vme@lgpc.cpe.fr, tel: +33 (0)4 72 43 17 55 - Fax: +33 (0)4 72 43 16 73

The deposition of TiO₂-P25 on Pyrex glass is studied in order to propose a procedure for obtaining uniform and adherent thin films with a controlled thickness in the range between fractions of micrometer to a few tens of micrometers. Different deposition methods such as spray-coating, dip-coating and drop-coating of liquid suspensions of TiO₂-P25 powder are considered. The effect of pretreatment of the glass support, as well as post-deposition steps such as drying condition and thermal treatment are also reported. A basic glass pretreatment and an acidic TiO₂ suspension are chosen for an optimized adherence of the film. Drop-coating, associated with a slow drying under 55% relative humidity and a high temperature thermal treatment is the method of choice to prepare coated glass slides in a large range of film thicknesses.

1 Introduction

TiO₂ is the most studied photocatalyst for reasons widely reported by consensus: better performances (Herrmann 2005), easy availability, low cost. Among the different sources of this material (synthesis or commercial), the commercial Aeroxide P25, produced by Evonik, is often the preferred one because of its high photocatalytic activity (Thevenet et al. 2005; Gaya and Abdullah 2008; Guillard et al. 2002). The use of structured reactors in photocatalytic applications implies the need to deposit a layer of TiO₂ on the structure, most of the time made of

glass because of its transparency to UV light allowing the source of photons to be located at the back. Back illumination of the glass may be useful when the liquid to treat is not transparent to UV light (presence of dusts, suspended matter, dark solution...). A comparative study of liquid-side irradiation and back-side irradiation can be found in the work of Vezzoli et al. (2013).

In many published works, the TiO_2 layer is directly synthesised on the glass from a titanium alkoxide sol to better adhere to the surface (Choi et al. 2006; Yun et al. 2004). The direct deposition of commercial P25 on glass has nevertheless been published by different research groups. Mills et al. (2006) prepared some P25-coated plates to study the photomineralization of soot. P25 was directly suspended in pure water, and the coated plates were only dried at moderate temperature (70°C). However, the coated material was not used in a liquid flow and the adherence was not a key parameter. Dijkstra et al. (2001), also using only water as the suspending P25 medium, concluded that the coating method had to be improved because considerable wash out of the catalyst was observed during photocatalytic experiments in liquid medium. To increase the adherence of P25 on glass, several additives have been proposed, the use of titanium alkoxide sol-gel being one of them, leading to a hybrid mixture sol/powder (Natarajan et al. 2011). Arabatzis et al. (2002) used a suspension made of P25, acetylacetone, Triton X100 and water that was displayed on glass plates by the doctor-blade technique. Sometimes P25 was mixed with a sol-gel of silica to improve the adherence, with (Chen and Dionysiou 2008) or without (Carbonaro et al. 2013) the addition of a surfactant. In the case of Kete et al. (2014), the hybrid mixture of P25 (or other sources of TiO_2) with a silica-titania binder was found to be very resistant to scratch tests, despite the low-temperature treatment of the layer (150°C).

In our laboratory, a previous study was carried out to coat some SiC structured substrates with TiO_2 P25 (Rodriguez et al. 2009). In the present work, the direct coating of this material on glass slides was studied. The objectives were to propose a simple method avoiding the use of organic additives and/or silica and providing uniform and adherent layers in a wide range of thicknesses. For that purpose, the influence of the glass pretreatment, suspension content, deposition method, drying conditions were evaluated.

2 Experimental part

2.1 Material

Evonik Aeroxide TiO_2 (P25) was provided by Acros Organics. NaOH, acetone, isopropanol, ethanol and deionised water were used for glass pretreatment tests. Triton X100, polyethylene glycol 200 (PEG), ethylene glycol (EG),

acetylacetone (AA), ammonium polymethacrylate (Darvan C) and hydrochloric acid HCl were used as additives to the TiO₂ suspension. Pyrex glass slides (26 mm × 76 mm × 1.1 mm) were chosen as substrate because this material is mostly transparent to UV light for wavelength above 320 nm (extinction coefficient $\approx 0.52 \text{ cm}^{-1}$ from de Lasa et al. (2005)).

2.2 Analytical methods

Contact angle measurements were performed with a Kruss drop shape analyzer - DSA30. The sessile drop method was used for measurement.

A Dektak 150 (Veeco Instruments Inc.) profilometer was used to determine the thickness and roughness of the coated catalyst films. Before profilometry examination, a line was carefully scratched on the coated glass slides by a knife to show the surface of the glass support. The course of the diamond stylus was set to run orthogonally to the scratch line. The thickness of the catalyst film coated was obtained by the average height difference between the surface of coated catalyst layer and the surface of the glass support (revealed by scratching). The adherence of the TiO₂ layer was estimated by measuring the weight loss after 1 minute in heptane in an ultrasonic bath at room temperature (RT $\approx 20^\circ\text{C}$) according to Meille et al. (2005). A qualitative result of the adherence test is provided (“+”: adherence >80%, “-”: adherence <80%). An adherence >80% was indeed found sufficient to ensure a stability of the TiO₂ layer during one day of photocatalytic experiments ($\text{Re} \leq 800$).

2.3 Coating procedures

2.3.1 Preliminary steps

Different glass pretreatments and additives in the TiO₂ suspension were tested to get the highest adherence of the TiO₂ layer on the glass.

Glass pretreatment

The pretreatments consist in immersing the glass slides in a solvent during 30 minutes, either at RT in an ultrasonic bath or at a given temperature in a thermostated bath. The solvents tested were: acetone, ethanol, i-propanol and the temperature ranged from 20 to 45°C. Then, the plates were simply dried at room temperature after the organic pretreatments. In the case of basic pretreatments (NaOH), the glass slides were further rinsed with deionized water

and dried under air or N_2 using a temperature program with a ramp rising from 20°C to 500°C in 2 hours, a plateau at 500°C for 4 hours and a decrease to 100°C. Once removed from the oven at 100°C, they were weighed immediately. The objectives of this temperature program were to get the glass slide tare under controlled conditions (very clean and dry glass surface) required for accurately weighing small amounts of TiO_2 (few mg).

Preparation of the suspension

The suspensions were prepared by mixing TiO_2 , deionised water and the chosen additive (among those listed in paragraph 2.1) in an ultrasonic bath during 30 minutes. The TiO_2 concentration was in the range [1.5-75 g/L]. The particle size distribution in the suspension has been measured by Rodriguez et al. (2009). It is in the range [1-15 μ m]. Note that the TiO_2 concentration is very low, leading to suspension viscosities of the same order of magnitude as that of water.

2.3.2 Coating methods

Three coating methods were compared in terms of uniformity and range of thicknesses achieved.

Spray-coating

The spray-coating of the suspension was performed through a Sono-Tek microspray ultrasonic nozzle (10kHz). Three factors were studied: the TiO_2 concentration, the scanning speed of the nozzle and its distance to the glass support.

Dip-coating

The glass substrates were dipped into the prepared TiO_2 suspension for 5 seconds, withdrawn slowly (ca. 1 cm/s) and shaken to remove the excess of suspension. After that, one face of the coated glass slides was cleaned immediately to make sure that no TiO_2 remained.

Drop-coating

Drop-coating method was performed by pouring a controlled volume of suspension on the surface of the glass plate, set horizontally, using a plastic liquid dropper with suction bulb.

2.3.3 Post-treatment of the films

The post-treatment aims at obtaining adherent solid films without cracks. It involves two steps: a drying of the liquid film and a further thermal treatment of the solid deposit.

Drying

Once deposited, the films were first dried at room temperature. Different drying atmospheres at controlled humidity were obtained by using saturated salt solutions of NaCl, $\text{Mg}(\text{NO}_3)_2$ and MgCl_2 . The drying duration was from a few hours to several days, depending on the liquid film thickness and the relative humidity.

Thermal treatment

After drying, a thermal treatment step was performed under N_2 using a temperature program with a ramp rising from 20°C to 500°C in 2 hours, a plateau at 500°C for 4 hours and a decrease to 100°C. The aim of the thermal treatment was to remove the additives and to make the film adhere to the surface. Attempts to perform a thermal treatment at a lower temperature (350°C) resulted in a bad adherence of the layer. The coated glass slides were weighted just at the exit of the oven at 100°C, to avoid water adsorption.

3 Results and discussion

3.1 Preliminary steps

3.1.1 Effect of the glass pretreatment

[Table 1 about here]

Different chemical treatments of the glass slides were tested (Table 1). The influence of the glass pre-treatment on the uniformity and adherence of the TiO_2 layer was recorded. Contact angle measurements were also performed to characterize the spreading of the suspension on the glass surface. Only one suspension was selected for those measurements (Table 1). All the attempts with organic pre-treatment alone (i-propanol or acetone at RT or at 45°C, ethanol at RT) led to non-adherent layers, even if the spreading was satisfactory (contact angle of 40° with ethanol).

On the contrary, the basic pretreatment (NaOH 1M) at 90°C for 30 minutes gave some adherent layers, even with high contact angles of 85°.

3.1.2 Effect of additives in the suspension

The role of additives was expanded from the non successful test of sodium hexametaphosphate performed in the publication of Rodriguez et al. (2009). Amongst many organic additives tested, Triton X100, PEG, EG and AA gave a worse adherence of the TiO₂ layer than water alone (Table 1). On the contrary, Darvan C led to an increased adherence. The same improvement was also obtained with an acidification of the suspension by HCl 1M. In the latter case, the adherence on NaOH-treated plates was probably due to an acid-base interaction between the liquid and the surface. To avoid the presence of organic residues, the use of the acidified suspension was preferred.

In the next paragraphs, the procedure retained and used for all the experiments includes the following steps:

- the glass plates are first degreased 30 minutes in acetone in an ultra-sonic bath, then treated at 90°C for 30 minutes in NaOH 1M, rinsed and dried an aqueous suspension made of TiO₂ (1.5 to 75 g/L) in diluted hydrochloric acid (pH 2 to 3) is applied to the plates by the different coating methods described in section 3.2.

3.2 Effect of the deposition method

3.2.1 Spray-coating

Several glass plates have been spray-coated with three different suspensions (2.5, 7.5 and 15 g/L) at different spraying heights and different scanning speeds of the nozzle (in one single pass). Spray-coating allows to obtain thin layers but with a rather bad homogeneity of the film. The NaOH pretreatment leads to a bad spreading of the suspension on the surface. Then, a partial drying during spraying leading to isolated spots instead of a continuous film is sometimes encountered, depending on the temperature in the room. Thus, the spray doesn't result in an uniform film but rather to the juxtaposition of spots, which can eventually coalesce depending on the amount of the suspension and the drying conditions (see example in Figure 1).

[Figure 1 about here]

Two different models were used to try to predict the mass of TiO_2 of the coating from the shape of the spray, the distance nozzle-slide and the operating conditions, such as the flow through the nozzle (Q) and the scanning speed (v) (Figure 2).

[Figure 2 about here]

Assuming an uniform deposition of the suspension on the slides (of surface area $a = 19.7 \text{ cm}^2$) during the spraying, the mass of TiO_2 deposited can be derived for a conic spray with equation:

$$m = \frac{Qa}{v} \cdot \frac{2}{h \tan \theta} C_{\text{TiO}_2} \quad (1)$$

and for a parabolic one with:

$$m = \frac{Qa}{v} \cdot \frac{1}{\pi p \sqrt{h}} C_{\text{TiO}_2} \quad (2)$$

The use of these relations requires the preliminary determination of: a) the suspension flow rate, for each concentration of TiO_2 in the suspension, and b) the diameter of the sprayed area for different height of the nozzle above the glass slide for each concentration of TiO_2 which leads to the parameters $\tan \theta$ for the conic model and p for the parabolic model. The best model describing the effect of the concentration of TiO_2 in the suspension (2.5-15 g/L), the scanning speed of the nozzle (range 5-25 mm.s^{-1}) and the distance between the glass plate and the nozzle (25-55 mm) was the parabolic one (Figure 3).

[Figure 3 about here]

3.2.2 Dip-coating

[Figure 4 about here]

Suspensions from 2.5 to 30 $\text{g}_{\text{TiO}_2}/\text{L}$ have been applied on glass plates by dip-coating. Due to the high contact angle between the suspension and the glass surface, an uniform liquid film was not formed and the Landau-Levich-Derjaguin equation from de Ryck and Qur (1998) was not applicable. After drying, rinsing one side of the plate and thermal treatment, the mass obtained was found to increase slightly with the suspension concentration (Figure 4). The restricted variability of the mass and the very bad uniformity of the layer were found crippling for the use of that method (See photo inserted on Figure 4).

3.2.3 Drop-coating

The advantage of this method is that the mass of TiO_2 can be precisely predicted since the volume of suspension dropped on the glass slide set horizontally, and its TiO_2 concentration are known. The mass obtained can vary in a wide range depending on the volume spread over the slide surface (from a few drops to a few milliliters) and the concentration of TiO_2 in the suspension:

$$m = C_{\text{TiO}_2} V \quad (3)$$

A TiO_2 mass in the range [0.2-100 mg] was obtained. An illustration of the method and the resulting liquid film (before drying) is presented in Figure 5.

[Figure 5 about here]

3.3 Comparison of methods

3.3.1 Successive coatings

[Figure 6 about here]

Successive coatings have also been studied as a way to increase the TiO_2 mass on the plate (Figure 6). Attempts to simply treat the intermediate layers at 120°C led to less adherent layers (not presented). A thermal treatment at 500°C was necessary between each layer. Thus, despite the possibility to reach thick layers by successive coatings with dip- spray- or drop-coating, they were more easily and rapidly obtained by the drop-coating method, and the film was more uniform. The result of drop-coating may look similar to that of the doctor-blade technique, the former method being based on a self-leveling coating (non-viscous suspension), the latter depending on the leveling of the doctor-blade (Berni et al. 2004; Ngamsinlapasathian et al. 2006). The advantage of drop-coating vs. doctor-blade is that the exact amount of slurry deposited (and thus of TiO_2) is known.

3.3.2 Density of TiO₂

The mass of TiO₂ coated on the glass slides has been plotted vs. the thickness measured by profilometry for the different coating methods (Figure 7). A common linear tendency was found with a slope corresponding to a density of the coating of $1.64 \pm 0.04 \text{ g.cm}^{-3}$.

[Figure 7 about here]

This value is in good agreement with published values for TiO₂-P25 films (2 g.cm^{-3} from Baranova et al. (2007), 1.49 g.cm^{-3} calculated from Zhao et al. (2012)). It is far from the bed density of P25 powder (0.13 g.cm^{-3}) because of compaction of particles during coating but not far from the density of ideal compactness, 1.95 g.cm^{-3} , calculated from the crystal density of P25 (3.9 g.cm^{-3}) and the mesopore volume of the P25 powder (0.25 g.cm^{-3}), leading to a porosity of 0.5 (Porosity = mesopore volume/(mesopore volume + 1/crystal density) from Zhao et al. (2012)). The difference is likely due to the stacking (intergranular) porosity, which seems to be similar whatever the coating method. This similarity is not surprising since the suspension used and the drying/thermal treatment procedures are the same whatever the deposition method used.

3.4 Effect of the drying conditions

It is known that a slow drying avoids the formation of cracks and favours an uniform surface (Fabes et al. 1986). Therefore, different drying conditions at 20°C were tested to determine the appropriate humidity conditions to get a dry plate with an uniform coating. The influence of drying is maximised in the case of drop-coating since the amount of liquid deposited on the glass is higher. It was found that a drying at low humidity conditions (MgCl₂, 33% RH from Greenspan (1977)) was rapid and led to a non-uniform film with many waves (Figure 8, left). On the contrary, a drying in more humid atmospheres (Mg(NO₃)₂, 55% RH) or NaCl, 75% RH) led to uniform films (Figure 8, right). The RH provided by the use of Mg(NO₃)₂ was considered as a good compromise between uniformity and drying duration. However, adherence tests showed a high adherence of the solid film on the surface (> 80%), whatever the drying method.

[Figure 8 about here]

SEM pictures of the TiO₂ layer obtained by the different drying media are shown in Figure 9. It was confirmed that drying at intermediate relative humidity provides a more uniform layer, with limited cracks.

A good uniformity was also obtained by letting the plates dry slowly in the fridge (not shown), the key point being to avoid a fast drying. Several days were required to achieve the drying before the thermal treatment.

4 Conclusion

The coating of glass slides was carried out by different methods using an aqueous suspension of TiO_2 -P25 powder. To get a high adherence of the TiO_2 on the glass, a basic pretreatment of the surface, combined to the use of an acidic suspension were necessary. This combination was not favorable to spraying or to dip-coating, because of a high contact angle liquid/surface. In contrast, the drop-coating method was well-adapted to obtain an uniform film layer. A slow drying under wet conditions (55% RH) was the key to get an uniform solid film. After thermal treatment, all the coated plates, in the thickness range [0.03-40 μm], showed a similar solid film density of 1.64 g.cm^{-3} . The thickness was thus easily predictable thanks to the volume dropped and the concentration of the suspension. In a further work, the slides with deposited TiO_2 will be tested in a photocatalytic reaction in order to study the effect of the TiO_2 thickness on the photocatalytic activity.

5 Nomenclature

a surface area of the slide (m^2)

C_{TiO2} concentration of TiO_2 in the suspension (kg/m^3)

h height of the nozzle above the glass slide (m)

m mass of TiO_2 deposited on a single slide (kg)

p parameter for the spraying parabola ($\text{m}^{1/2}$)

Q flow rate of the suspension through the nozzle ($\text{m}^3.\text{s}^{-1}$)

r radius of the sprayed discus (m)

V Volume of suspension deposited by coating (m^3)

v scanning rate of the nozzle or withdrawal rate from a suspension (m.s^{-1})

θ half angle of the spraying cone

References

- Arabatzis, I. M., S. Antonaraki, T. Stergiopoulos, A. Hiskia, E. Papaconstantinou, M. C. Bernard, and P. Falaras. 2002. Preparation, characterization and photocatalytic activity of nanocrystalline thin film TiO_2 catalysts towards 3,5-dichlorophenol degradation. *J. Photochem. Photobiol., A* 149, 237–245.
- Baranova, E. A., G. Foti, H. Jotterand, and C. Comninellis. 2007. Electrochemical modification of the catalytic activity of TiO_2 /YSZ supported rhodium films. *Topics in Catalysis* 44(3), 355–360.
- Berni, A., M. Mennig, and H. Schmidt. 2004. Doctor blade. In *Sol-Gel Technologies for Glass Producers and Users* ed. by M. A. Aegerter and M. Mennig, pp. 89–92. Springer US.
- Carbonaro, S., M. N. Sugihara, and T. J. Strathmann. 2013. Continuous-flow photocatalytic treatment of pharmaceutical micropollutants: Activity, inhibition, and deactivation of TiO_2 photocatalysts in wastewater effluent. *Applied Catalysis B: Environmental* 129, 1–12.
- Chen, Y. and D. D. Dionysiou. 2008. Bimodal mesoporous TiO_2 -P25 composite thick films with high photocatalytic activity and improved structural integrity. *Appl. Catal., B* 80, 147–155.
- Choi, H., E. Stathatos, and D. D. Dionysiou. 2006. Synthesis of nanocrystalline photocatalytic TiO_2 thin films and particles using sol-gel method modified with nonionic surfactants. *Thin Solid Films* 510, 107–114.
- de Lasa, H., B. Serrano-Rosales, and M. Salaices-Arredondo. 2005. In *Photocatalytic Reaction Engineering*. Springer. ISBN 0-387-23450-0.
- de Ryck, A. and D. Quéré. 1998. Gravity and inertia effects in plate coating. *Journal of Colloid and Interface Science* 203(2), 278–285.

- Dijkstra, M. F. J., H. Buwalda, A. W. F. de Jong, A. Michorius, J. G. M. Winkelman, and A. A. C. M. Beenackers. 2001. Experimental comparison of three reactor designs for photocatalytic water purification. *Chem. Eng. Sci.* 56, 547–555.
- Fabes, B. D., W. F. Doyle, B. J. J. Zelinski, L. A. Silverman, and D. R. Uhlmann. 1986. Strengthening of silica glass by gel-derived coatings. *Journal of Non-Crystalline Solids* 82(13), 349–355.
- Gaya, U. I. and A. H. Abdullah. 2008. Heterogeneous photocatalytic degradation of organic contaminants over titanium dioxide: A review of fundamentals, progress and problems. *J. Photochem. Photobiol., C* 9, 1–12.
- Greenspan, L. 1977. Humidity Fixed Points of Binary Saturated Aqueous Solutions. *Journal of Research of the National Bureau of Standards - A. Physics and Chemistry* 81A(1), 89 – 96.
- Guillard, C., B. Beaugiraud, C. Dutriez, J. M. Herrmann, H. Jaffrezic, N. Jaffrezic-Renault, and M. Lacroix. 2002. Physicochemical properties and photocatalytic activities of TiO₂-films prepared by sol-gel methods. *Appl. Catal. , B* 39, 331–342.
- Herrmann, J. M. 2005. Heterogeneous photo-catalysis : state of the art and present applications. *Topics in Catalysis* 34 (1-4), 49–65.
- Kete, M., E. Pavlica, F. Fresno, G. Bratina, and U. L. Stangar. 2014. Highly active photocatalytic coatings prepared by a low-temperature method. *Environmental Science and Pollution Research* 21(19), 11238–11249.
- Meille, V., S. Pallier, G. V. Santa Cruz Bustamante, M. Roumanie, and J.P. Reymond. 2005. Deposition of layers on structured supports for the design of new catalytic reactors. *Appl. Catal. A* 286, 232–238.
- Mills, A., J. Wang, and M. Crow. 2006. Photocatalytic oxidation of soot by P25 TiO₂ films. *Chemosphere* 64, 1032–1035.

- Natarajan, K., T. S. Natarajan, H. Bajaj, and R. J. Tayade. 2011. Photocatalytic reactor based on UV-LED/TiO₂ coated quartz tube for degradation of dyes. *Chemical Engineering Journal* 178, 40–49.
- Ngamsinlapasathian, S., A. Kitiyanan, T. Fujieda, and S. Yoshikawa. 2006. Effects of substrates on Dye-Sensitized solar cell performance using nanocrystalline TiO₂. *ECS Transactions* 1 (33), 7–15.
- Rodriguez, P., V. Meille, S. Pallier, and M. A. Al Sawah. 2009. Deposition and characterisation of TiO₂ coatings on various supports for structured (photo)catalytic reactors. *Appl. Catal., A* 360, 154–162.
- Thevenet, F., O. Guaitella, J. M. Herrmann, A. Rousseau, and C. Guillard. 2005. Photocatalytic degradation of acetylene over various titanium dioxide-based photocatalysts. *Applied Catalysis B: Environmental* 61(12), 58–68.
- Vezzoli, M., T. Farrell, A. Baker, S. Psaltis, W. N. Martens, and J. M. Bell. 2013. Optimal catalyst thickness in titanium dioxide fixed film reactors: Mathematical modelling and experimental validation. *Chemical Engineering Journal* 234, 57–65.
- Yun, Y. J., J. S. Chung, S. Kim, S. H. Hahn, and E. J. Kim. 2004. Low-temperature coating of sol-gel anatase thin films. *Mater. Lett.* 58, 3703–3706.
- Zhao, X., H. Lin, Y. Liu, X. Li, P. Yang, H. Chen, G. Wang, and J. Li. 2012. The effect of dispersion of TiO₂ nanoparticles on preparation of flexible dye-sensitized photoanodes. *Science China Physics, Mechanics and Astronomy* 55(7), 1203–1209.

Figure 1: Example of one spray-coated glass slide

Figure 2: Shape of the spray for a) the conic model, b) the parabolic model

Figure 3: Spray-coating experiments at different TiO₂ concentrations (Scanning speed = 16 mm/s) - Comparison of parabolic and conic models

Figure 4: Effect of TiO_2 loading in the suspension in the case of dip-coating method

Figure 5: Drop-coating method and resulting liquid film

Figure 6: Mass of TiO_2 layer obtained by successive coatings of a 7.5 g/L TiO_2 suspension
by spray-, dip-, and drop-coating

Figure 7: Mass vs. thickness for the three coating methods, with 1 to 6 successive layers

Figure 8: TiO_2 drying in air of a drop-coated layer at 33% RH (left), air at 55% RH (middle)
and air at 75% RH(right)

Figure 9: SEM pictures of TiO_2 layer dried in air at 33% RH (left), air at 55% RH (middle) and air at 75% RH(right)

Glass treatment	Temperature	Additives	Contact angle	Adherence
Acetone	RT	no	40°	-
Acetone	RT	PEG		-
Acetone	RT	EG		-
Acetone	RT	HCl		-
Acetone	RT	AA		-
Acetone	40°C	no		-
Ethanol	RT	no	85°	-
i-Propanol	RT	no		-
i-Propanol	45°C	no		-
NaOH	90°C	no		-
NaOH	90°C	Darvan C		+
NaOH	90°C	Triton X100		-
NaOH	90°C	HCl 1M		+
NaOH	90°C	PEG		-
NaOH	90°C	EG		-
NaOH	90°C	AA		-

Table 1: Effect of glass pretreatments and additives on the qualitative adherence of the TiO₂ layer