Local study of the corrosion kinetics of hardened Portland cement under acid attack

Héloïse Gay, Thomas Meynet, Jean Colombani

*Institut Lumière Matière; Université de Lyon; Université Claude Bernard Lyon 1;
CNRS, UMR 5306; Domaine scientifique de la Doua, F-69622 Villeurbanne cedex,
France*

Abstract

Whereas the chemical reactions occurring during the acid corrosion of cementitious materials are now well known, their reaction rate have still not been measured. We propose here a methodology using digital holographic interferometry to access to the pure surface reaction rate. This method makes possible the differentiation between the dissolution and precipitation steps. We use it to measure the reaction rate constant of the dissolution of hardened Portland cement in aqueous solutions of nitric, sulfuric and hydrochloric acid at pH 2. This quantity is seen to be unexpectedly similar for the three acids, with a value of the order of $1 \text{ mg/m}^2/\text{s}$. We have measured the evolution of this reaction rate constant with the pH in nitric acid. We have also measured the real pH of the solution at the material surface, which is always alkaline ($\text{pH} > 11$), even for attacks by solution with pH as low as 1.

Keywords: A: reaction, A: kinetics, A: pH, C: corrosion, acid

1. Introduction

The extension of the durability of concrete buildings necessitates the understanding of its limiting factors, like creep, crack propagation by water freezing, degradation due to aggressive environments, etc. Among chemical attacks reducing the service life of construction materials, acid attack is particularly detrimental to materials as alkaline as cementitious materials.

Email address: Jean.Colombani@univ-lyon1.fr (Jean Colombani)

7 Indeed the hydration products of cement are neutralized by protons, induc-
8 ing dissolution and precipitation of new salts, destroying the microstructure
9 of this hydraulic binder. The mechanisms of action of acid reagents on con-
10 crete, mainly originating outdoor in air pollution (dry deposition) and acid
11 rains (wet deposition), have been investigated for a few decades, and the
12 basic features are now identified [1, 2, 3]. These modes of action have also
13 been studied indoor in the case of industrial constructions involving acidic
14 environments [4, 5]. These mechanisms, including heterogeneous reactions,
15 ion substitution, mass loss, diffusion of solution in pores, strain, porosity
16 evolution, leaching, etc. are complex, interact with each other, and lead to
17 a loss of strength and stiffness of the material.

18 The investigation of acid attack on cement-based materials has been
19 performed either with field measurements in urban areas [6, 7], or with
20 laboratory measurements. The latter have used either simulated acid rain
21 solutions [7, 8, 9], or concentrated acid aqueous solutions [10], in order to
22 accelerate the reactions. Sometimes, different reagents are tested simultane-
23 ously or alternatively [10, 4]. In the course of these studies, three parameters
24 are generally evaluated: the chemical composition of the runoff solution, the
25 change of mass or size of the samples, and their strength decrease. Due to
26 the complexity of the phenomenon, a quantity is generally not measured, al-
27 though being the fundamental parameter of chemical kinetics: the reaction
28 rate.

29 Up to now, models of degradation of concrete under acid attack use em-
30 pirical dissolution laws [11]. We think that the knowledge of well-defined
31 reaction parameters may help in the elaboration of the predicting tools of
32 acid corrosion. As the reaction of dissolution is always combined with other
33 phenomena like precipitation, flow of the solution, diffusion of dissolved
34 species, etc. in standard acid attack setups, these experiments are not us-
35 able for pure corrosion rate measurement. Therefore we propose in this
36 article an original methodology, using holographic interferometry, to access
37 to the reaction rate of cementitious materials in acid solutions. We provide
38 values of the pure dissolution rate of hardened Portland cement in three
39 strong acids —nitric, sulfuric and hydrochloric acids— at various pH as first
40 examples of measurements.

41 Our investigation of hydrated cement acid attack follows a non-conventional
42 procedure, focusing on one single step of the phenomenon, namely on the
43 first one, dissolution. Accordingly a comparison of our results with standard
44 studies on the resistance of cement-based materials to acid is not directly
45 possible [12]. Indeed these experiments are global ones, including dissolu-
46 tion, precipitation, cracking, volume expansion ... and do not enable to

CaO	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Na ₂ O	MgO	K ₂ O	SO ₂
62.7	17.7	5.5	4.1	0.4	0.8	0.7	3.7

Table 1: Composition (mass %) of the ordinary Portland cement used in the corrosion experiments.

isolate pure dissolution. But we hope that our main results —values of the reaction rates, real value of the pH at the attacked surface, evidence of the tiny influence of the nature of the strong acid— will (i) find verification in standard studies, and (ii) help to model more accurately acid degradation of cementitious materials.

2. Materials and method

2.1. Samples and acidic solutions

We have used in this study ordinary Portland cement (CEM-1), the composition of which is detailed in table 1. It is made of at least 95% clinker. The cement paste was cast in Petri dishes and cut, after 28 days of curing in a moist environment, in order to obtain parallelepipedic samples of approximate dimensions $5 \times 5 \times 0.5$ mm³. The water over cement ratio was 0.4. The nitric, sulfuric and hydrochloric acid solutions were diluted with pure water to obtain the required pH. These three inorganic acids being strong, the pH is the convenient quantity to indicate the content of aggressive species in solution. All experiments have been carried out at ambient temperature.

2.2. Holographic interferometry

Our final aim is the measurement of a reliable reaction rate of hardened cement in acid solutions. To be unquestionable, the experiments must guarantee that no other phenomenon (convection, precipitation . . .) disturbs the measurement, to provide a pure dissolution rate. This implies that, during the acid attack of the samples, we are able (i) to observe the interface where the reaction proceeds, to study the reaction precisely where it occurs, and (ii) to access to the concentration field in the liquid soaking the solid, in order to detect all possible mass transport phenomena (diffusion, convection) and remove their contribution from the reaction rate. To achieve these two goals, we have carried out real-time digital holographic interferometry measurements.

Figure 1: Photograph and diagram of the experimental cell, containing the acid solution and the hardened cement sample at the bottom.

Here we take advantage of the potentiality of holography to record phase objects, i.e., transparent objects exhibiting only variation of their index of refraction in our case. Here the investigated transparent object is the solution where the solid dissolves, contained in a transparent cell of dimensions $10 \times 10 \times 40 \text{ mm}^3$ (figure 1). We record first the state of this corrosive liquid in a so-called reference digital hologram at time t_0 . Here, we choose for t_0 the moment just before the solid is introduced in the cell. Then the hardened cement thin sample is placed at the bottom of the cell. Subsequently we record periodically the digital hologram of the liquid during the attack of the solid. Afterwards we perform numerically a superposition of the holograms at time t_0 and at the various times t to obtain interferograms of the evolution of the state of the liquid between times t_0 and t (figure 2). The evolution of the concentration c in the solution, due to the ion release stemming from the attack, induces a change of the refractive index, hence of the phase of the liquid, which is visualized through interference fringes. We want to emphasize that holographic interferometry differentiates from classical interferometry in the fact that no external reference is needed, the object interfering virtually with a memory of itself [13].

A numerical procedure enables to reconstruct the two-dimensional concentration field in the liquid from the fringes (figure 3). As only concentration changes inside the cell here, and the concentration was initially uniform, interference fringes are iso-concentration curves. The fringes have always been observed horizontal, so we can deduce that concentration is horizontally invariant, and the evolution is only one-dimensional, in the vertical direction.

The chemical reaction is considered first-order, with the dissolution flux at the interface writing $J = ks_r(1 - c/s)$ with k the reaction rate constant, s_r the reactive surface area, c the concentration of the dissolved species and

Figure 2: Digital holographic interferograms of the dissolution of a hardened Portland cement sample at the bottom of a nitric acid solution of pH 1.5, at 5, 15, 30, 50, 80, 130, 220, 400 and 600 min after the introduction of the sample at the bottom of the cell. The dimension of each interferogram is $5 \times 18 \text{ mm}^2$.

104 s their solubility limit. The two physico-chemical quantities s and k both
 105 depend on the thermodynamic conditions, the sole varying parameter of
 106 which here is the pH. The reaction rate J can be viewed as the velocity with
 107 which the concentration curve at the interface $z = 0$ shifts upward (figure
 108 3).

The solution of Fick's second law with this chemical reaction at the solid-liquid interface, in a semi-infinite one-dimensional approximation, brings the theoretical concentration evolution $c(z, t)$ with vertical dimension z and time t in the cell:

$$c(z, t) = s \left[\operatorname{erfc} \left(\frac{z}{2\sqrt{Dt}} \right) - \exp \left[\frac{k(s_r/s_d)z}{D\rho s} + \left(\frac{k(s_r/s_d)}{D\rho s} \right)^2 Dt \right] \times \operatorname{erfc} \left[\frac{z}{2\sqrt{Dt}} + \frac{k(s_r/s_d)}{D\rho s} \sqrt{Dt} \right] \right] \quad (1)$$

109 with s_d the section of the experimental cell, ρ the density of the solution,
 110 and D the diffusion coefficient of the dissolved species. The best fit of the
 111 experimental curves deduced from the holographic results with the analytic
 112 expression of $c(z, t)$ brings the pure surface reaction rate constant k , the
 113 solubility of the dissolved species s , and their mean diffusion coefficient D
 114 (figure 3).

115 We stress on the fact that the solubility s measured here is the saturation
 116 concentration of the dissolving components of hardened cement (see section
 117 3 for the nature of these components). This solubility has no link with the
 118 components precipitating later in the course of the experiment.

119 Details on the experimental device and data analysis have been given
 120 elsewhere, applied to the situation of gypsum dissolution in water [14] and

Figure 3: Experimental (black curves) and theoretical (red curves) concentration of dissolved cement hydrate in a nitric acid solution of pH 1.5 versus vertical dimension. The curves correspond to the times 9, 15, 25, 35, 47, 70, 100, 150, 190, 250 and 350 min of the experiment. The horizontal line is the extrapolated saturation concentration s of the dissolved species. The sample lies at $z = 0$.

121 in various aqueous solutions [15].

122 This method of investigation of hydrated cement corrosion by acid solu-
123 tions brings the following advantages:

- 124 1. The observation of the two-dimensional concentration field in the liq-
125 uid enables to state that the mass transport of the dissolved species
126 in our quiescent liquid is exclusively diffusional, thereby validating the
127 use of Fick's law to determine the theoretical concentration profile.
128 Indeed, the presence of any non-diffusive fluxes (natural convection,
129 gravitational instability ...) would have induced a distortion of the
130 interference fringes [16].
- 131 2. After a first step of pure dissolution, precipitation of salts stemming
132 from the neutralization of the mineral occurs [1]. The pure dissolu-
133 tion rate can be estimated from the concentration curves only before
134 this recrystallisation sets in. The holographic interferometry offers

Figure 4: Evolution with time of the concentration of dissolved hardened cement at the solid-liquid interface $z = 0$ during the dissolution of a hardened Portland cement sample at the bottom of a nitric acid solution of pH 1.5.

the chance to follow the concentration at the solid-liquid interface $c(z = 0, t)$. In figure 3, this value can be read at the ordinate axis. It evolves upward due to the matter release caused by the attack. Precipitation consumes ions and thereby induces a decrease of the interface concentration. Therefore, as soon as $c(z = 0, t)$ decreases, the corresponding concentration curves are excluded from the fitting, to assure that only dissolution is taken into account. An example of concentration evolution with time at the interface during dissolution is shown in figure 4. In this case, the curves have been taken into account for the computation of the reaction rate constant only before the beginning of the plateau, at time $t \simeq 4$ h.

3. The good agreement between the experimental curves and the theoretical law constitutes a validation of our assumption that what occurs is a pure dissolution phenomenon with a first-order reaction.

2.3. Refractive index of the solution

The holographic interferometry device provides a two-dimensional phase map $\phi(y, z)$. The transformation of the phase into concentration has two requirements. First, the concentration must be known in each interferogram

Figure 5: Index of refraction of an aqueous solution of nitric acid of pH 1 *vs* concentration of dissolved hardened Portland cement. The line is a linear fit.

at least in one point, the rest of the absolute concentration field being de-
 duced by comparison with this point. As the initial liquid is the pure acid
 aqueous solution, free from dissolved matter, the concentration at the top
 of the cell is always $c = 0$. This is always true because, during the course
 of our experiments, we pay attention to the fact that no fringe has the
 time to reach the top of the cell. Secondly, the concentration is computed
 from the phase ϕ via the formula $c = \lambda\phi/[2\pi e(\partial n/\partial c)]$, where λ is the laser
 wavelength ($\lambda = 532$ nm), e the depth of the cell ($e = 10$ mm) and n the
 refractive index of the solution. The variation of the index of refraction of
 the solution with the concentration of dissolved species $\partial n/\partial c$ is therefore a
 crucial parameter. To gain this value, we have dissolved various quantities
 precisely weighed of finely ground hardened cement in pure aqueous solution
 of nitric acid of pH 1. Then we have measured the refractive index of this
 solution with an Abbe refractometer (figure 5). The slope of the $n(c)$ curve
 is the searched parameter $\partial n/\partial c = 2.4 \times 10^{-4}$ L/g.

We have measured the reaction rate of hydrated cement under acid at-
 tack at different pH. So to estimate the influence of pH on $\partial n/\partial c$, the refrac-
 tive index of an aqueous solution of pure nitric acid for various pH has been
 measured with the Abbe refractometer. It can be seen in figure 6 that the
 index of refraction is constant, except for very small pH, where it increases
 of 0.2%. In these conditions, we have estimated that the influence of the pH
 on $\partial n/\partial c$ is negligible.

Figure 6: Index of refraction *vs* pH of an aqueous solution of nitric acid.

3. Reactions during acid attack

Sulfuric, hydrochloric and nitric acids have been chosen because they are ones of the main acidic components in acid rains [6]. The chemical reactions of hydrated cement in these acid solutions have already been studied in detail. As our aim is not to discuss these reactions but to measure their kinetics, we will just recall them briefly. Under acid pH, all the constituents (calcium hydroxides, calcium silicate hydrates (CSH), calcium aluminate hydrates (CAH) . . .) dissolve at various velocities, and new salts precipitate. The first and faster dissolving component is calcium hydroxide –also called Portlandite– along the neutralization reactions [7]:

The nature of the calcium salts crystallizing subsequently depend on the anion provided by the acid, typically gypsum and ettringite in the case of sulfuric acid. The severity of the attack is considered to be mainly dependent on the solubility of the precipitated salts. Indeed in the case of highly insoluble salts, e.g. fluoride salts, a dense layer forms at the interface, protecting the material [2]. But to try to understand more clearly the mechanisms at the beginning of the attack, we have restricted ourselves in this study to the first stage of the acid attack, where the main phenomenon is the dissolution of Portlandite, and we have not studied the subsequent precipitation of possibly protecting layers. Therefore we access here to the pure severity of the acid attack, whatever the further reactions.

Figure 7: Concentration of dissolved calcium (red circles) and silicon (green squares) as a function of time during the attack of hardened Portland cement by quiescent nitric acid at $\text{pH} = 2$, measured with ICPAES.

196 To assess that the reaction scenario is really the above-mentioned one,
 197 we have performed additional chemical analyses of the attacked surface and
 198 of the soaking solution. The surface measurements have been carried out
 199 with the energy dispersive X-ray spectrometer (EDS) of a scanning electron
 200 microscope (SEM) and have brought the *post mortem* concentration of the
 201 main elements (Si, Ca, Al, Na, Mg, K, Ti, Mn, Fe) at the hardened cement
 202 surface after various attack durations. The solution measurements have
 203 been achieved with induced coupled plasma atomic emission spectroscopy
 204 (ICPAES) and enabled to access to the silicon, aluminum and calcium con-
 205 centrations in the solvent after some attack durations. The solution has been
 206 stirred before sampling to guarantee the homogeneity of the concentrations.

207 The evolution with time of the calcium and silicon concentration in the
 208 attacking solution during an experiment is shown in figure 7. Besides, the
 209 time change of the concentration of calcium and silicon at the surface of
 210 the attacked hardened cement during the same experiment are presented in
 211 figure 8. The calcium concentration is seen to decrease at the solid surface
 212 and to increase in the liquid. Oppositely, the silicon concentration increases
 213 slowly at the surface and remains almost zero in the solution. These four

Figure 8: Concentration of calcium and silicon atoms (in percentage of total elements) *vs* time at the surface of the attacked hardened cement of figure 7, measured with SEM EDS.

features are in perfect agreement with the above-explained expected attack mechanism. The fastest dissolving component is Portlandite, so calcium atoms progressively disappear from the surface and calcium ions are released in the acid solution. On the other side, CSH dissolves orders of magnitude slower than Portlandite and the release of silicon ions in the solution is almost negligible during the course of our experiment. As surface Portlandite fade away, CSH is uncovered and the concentration of silicon at the very surface increases.

Except aluminum, the concentration of all other elements at the attacked surface is 1% or below during the experiment. The surface concentration of aluminum is 5% and remains constant during the attack duration. The concentration of aluminum in the solution during the experiment is always about 1 mg/l, close to the measurement uncertainty. These results show that CAH, like CSH, is not affected by the attack for the duration of our experiment.

We wish to finish this section about the chemical reactions during the attack by mentioning that we have omitted a fundamental aspect of the reaction. Indeed the heterogeneous and evolving nature of the reactive sur-

face has been observed to be highly influential on the reaction kinetics of minerals [17]. But as nothing has been measured yet in hardened cement attacked by acid concerning the possible disparities of reaction kinetics of individual components, we have considered a constant and uniform reactive surface area, which has enabled to fit perfectly the experimental concentration curves.

4. Validation of the holographic procedure

As measurements of pure reaction rates had not been performed up to now, the comparison of our values with other ones, in order to validate them, is not possible for the moment. Indeed, existing studies usually present overall matter loss, including dissolution, precipitation and mass transfer in the solution and inside the porous solid. Therefore the comparison with material loss by pure dissolution is not directly possible. But to enable a future possible link with standard studies of acidic attack of cement-based materials, we have measured the mass loss of our samples during the experiments. To do so, we have dried the attacked platelets at 100°C during 2 h, then weighed them. From this and their initial mass, we have computed their mass loss due to the acid attack. Beside, we have estimated this mass loss from the numerical integration of the holographic concentration curve at the last investigated time (just preceding precipitation). As seen in figure 9, the measured and computed values of the mass loss compare well, thus validating the holographic procedure. This check attests that the total quantity of damaged material can then be deduced from the holographic measurements.

To further assess the accuracy of the holographic method, we have also compared the evolution of the quantity of dissolved calcium during the attack, as measured by ICPAES, with the evolution deduced from the numerical integration of the concentration curves measured by holointerferometry, considering that only Portlandite dissolves. As seen in figure 10, both evolutions compare well, the holographic measurements reflect quite quantitatively the progressive release of ions in the solution.

These two agreements between holography and standard measurements validate our methodology and our measured reaction rate constants.

5. Holographic results

Figure 11 displays the evolution of the solubility limit of hardened Portland cement in a pure aqueous solution of nitric acid for various pH obtained by holointerferometry. The quantities of matter are expressed as moles of

Figure 9: Mass of hydrated cement dissolved in nitric acid at the end the holographic experiment as a function of pH: measured mass (black circles) and estimated mass from the holographic measurements (red diamonds).

268 Portlandite (molar mass $M = 74 \text{ g/mol}$), the latter being the only con-
 269 stituent contributing significantly to dissolution (section 3).

270 As our measurements are nonstandard ones, we first detail the signifi-
 271 cation of the found solubilities. If Portlandite is considered to be in ex-
 272 cess, the saturation calcium concentration and pH should be fixed by the
 273 solubility product K_s of the reaction $\text{Ca}(\text{OH})_2 \rightarrow \text{Ca}^{2+} + 2\text{OH}^-$. As
 274 $K_s = [\text{Ca}^{2+}]_{\text{sat}}[\text{OH}^-]_{\text{sat}}^2 = 10^{-5.435}$ and the reaction releases at the same
 275 time one calcium and two hydroxide ions, the saturation calcium concentra-
 276 tion is $s = [\text{Ca}^{2+}]_{\text{sat}} = (K_s/4)^{1/3} = 10 \text{ mmol/L}$ and the final pH is 12.3. We
 277 have added this solubility of calcium in figure 11 as a dashed line. We see
 278 that, from pH 2 on, the saturation concentration of the hardened cement
 279 corresponds to the one of Portlandite in the case where the pH is freely fixed
 280 by the reaction equilibrium.

281 We want to stress on the fact that this solubility s is the saturation
 282 concentration of calcium in equilibrium exclusively with solid Portlandite,
 283 and does not take into account the solubility of other salts precipitating later
 284 in the experiment. Subsequently nitrate salts precipitate, and the solubility
 285 of calcium is modified accordingly, being in equilibrium with at least two

Figure 10: Time evolution of the dissolved calcium mass measured by ICPAES (black circles) and estimated from the holographic measurements (red diamonds) during the attack of hardened cement by nitric acid at $\text{pH} = 2$.

solid components (Portlandite and a nitrate salt). For instance in figure 4 the concentrations after 5 h, the time where the calcium concentration starts to decrease due to precipitation, are excluded from the computation of s , which is thereby only characteristic of the Portlandite/solution chemical equilibrium.

Two inferences may be drawn from the nature of the $s(\text{pH})$ curve in figure 11. First this is a new corroboration of the fact that Portlandite is here the only dissolving component. Secondly it shows that the pH of the solution at the interface is not the bulk solution pH , but a pH fixed by the reaction equilibrium, i.e., $\text{pH}_{\text{surf}} = 14 + \frac{1}{2} \log(K_s/s)$. This surface pH has been added in figure 11. It is observed to be always very alkaline, higher than 11, even for a bulk solution pH as low as 1. The interface pH takes the equilibrium value fixed by the reaction (12.3) for a bulk $\text{pH} \geq 2$. Below this value, the dissolution kinetics is too fast, compared to the diffusion kinetics, for the equilibrium value to be kept. Whereas the modification of the pH of the acidic solution in contact with the solid by the cement dissolution was expected, the novelty lies in the fact that this pH can be accurately measured, which enables a precise knowledge of the condition of

Figure 11: Evolution of the saturation concentration of hardened Portland cement in aqueous solutions of pure nitric acid (black circles) and evolution of the pH at the interface (red squares) with the pH of the bulk solution. The values of concentration are in moles of Portlandite per Liter of solution. The dashed line is the saturation concentration of Portlandite in the case that it freely fixes the final pH.

Acid	k		s	
	(mg/m ² /s)	(mmol/m ² /s)	(g/L)	(mol/L)
Hydrochloric	2.6	0.035	0.9	0.012
Nitric	2.0	0.027	0.9	0.012
Sulfuric	3.1	0.042	1.0	0.014

Table 2: Pure surface reaction rate constant k and solubility of the dissolved hardened cement s for the dissolution of hardened Portland cement in aqueous solutions of various acids for pH = 2. Values are expressed both in mass of dissolved hardened cement and in moles of dissolved Portlandite.

the damaging of the cementitious material surface.

Figure 12 (top) displays the evolution of the dissolution rate constant of hardened Portland cement in nitric acid as a function of the pH of the bulk solution. Again the quantity of matter is expressed in moles of Portlandite. The bulk pH is the pH of the initial acidic solution, far from the solid-liquid interface. But as has been evidenced in figure 11, the pH close to the interface has been thoroughly modified by the fast release of the OH⁻ due to the reaction. Therefore paradoxically these reaction rate constants are in fact characteristic of the behavior of the material in very alkaline conditions. We have related in figure 12 (bottom) the rate constants to the true pH they are characteristic of.

These results may appear puzzling. Indeed to predict the behavior of a cementitious material during an acidic attack at pH 1, the value of the reaction rate constant that should be used is the value at pH 11.5. This is due to the fact that for a heterogeneous reaction, a mass transport boundary layer develops in the vicinity of the solid. When the dissolution flux and the diffusion flux in this layer are of the same order of magnitude (the mixed kinetics regime), both interact and the concentration and the pH at the interface take out of equilibrium values (see a detailed situation in [18]).

Table 2 displays the reaction rate constant and saturation concentration of hardened Portland cement in pure aqueous solutions of nitric, sulfuric, and hydrochloric acids at pH = 2. We have expressed the quantities of matter in moles of Portlandite and in grams of hardened cement. As for nitric acid, the solubility of hardened cement in sulfuric and hydrochloric acid corresponds to the solubility of Portlandite free to fix the pH. Therefore the pH of the solution close to the surface for these two acids is likely to be also strongly alkaline, as in figure 11.

We see that the behavior of the material is similar in the three acid

Figure 12: Evolution of the dissolution rate constant of hardened Portland cement in aqueous solutions of pure nitric acid with the bulk pH of the solution (top) and with the surface pH deduced from the local solubility (bottom). The values are in millimoles of Portlandite per unit surface and time.

solutions, with values of k ranging within 25% from each other. We would like to emphasize that the fact that the reaction rate constants are highly similar for the three investigated acids is opposite to what is expected from conventional studies [10, 2]. This result demonstrates thus firmly that the kinetics of acid corrosion originates mainly in the precipitation step of the reaction. At this stage, a more or less protective layer progressively covers the surface, modifying the ion detachment rate, whereas before the formation of this layer, the kinetics of all acids are comparable.

Finally, we would like also to recall that our method enables to perform a real-time measurement of the spatially resolved reacting system. Therefore, we have been able to discriminate temporally the dissolution from the precipitation. As seen in figure 4, the time before precipitation sets in, i.e., the time before concentration decreases, is roughly 5 h. This order of magnitude has been observed in all our experiments. It gives an idea of the required time before precipitation proceeds in an unstirred acid. It is linked to the time needed for the interface concentration to reach the solubility of the precipitating salts.

6. Implications for hardened cement resistance to acid

As above-recalled, a diffusional boundary layer always builds up over a dissolving solid. In the case of a flowing liquid, this layer shows a thickness of the order of tens of μm [18]. In a quiet liquid, the final boundary layer thickness is theoretically infinite. The interface concentration and pH depend on this thickness: the pH will always remain close to 12, and the concentration will range between 0 and $s(\text{pH})$, for instance 0.22 mol/L for pH 1, depending on the relative kinetics of dissolution and diffusion. In the case of acid rain, once the material is wet, it is exposed to a quiescent solution and we are close to the hydrodynamic situation of our experiments. The only difference lies in the geometry, the degradation occurring at the surface and inside the pores, with sizes much smaller than the one of our cell.

Contexts in the laboratory and in real buildings being similar, what can we learn from our experiments for future studies? We propose three investigation directions:

- First, we dispose now of a tool to access the reaction rate of hardened cement in acid. So beside the study of protective layers precipitating after the dissolution step (ettringite ...), the formulation of materials with low reaction rates can also help to manufacture more durable

concrete. Recent measurements of the dissolution rate of hardened cement at alkaline pH show that the Ca/Si ratio can be optimized to lower this rate. This ratio is likely to influence also the kinetics of acidic attack [19].

- Numerical models of the degradation of concrete in acidic solution make use of empirical laws for the simulation of the dissolution step, rigorous thermochemical parameters being usually not accessible. We have shown here that a nonstandard method can give access to the exact reaction kinetics and we think that the integration of such experimentally-verified laws inside the models can bring a more realistic representation of damaging situations. We would like to emphasize that, even when precipitation sets in, the dissolution rate constants that we have measured before this precipitation, are still valid, being thermodynamically characteristic of the kinetics of the dissolution.
- At last, for industrial situations with harsh acid conditions, where the material is for instance exposed to a long-lasting acidic attack, cement-based materials have to be adapted to this stringent environment. In this case, the introduction in the formulation of admixtures known for their strong adsorption at the hardened cement surface, related to their calcium-complexing nature, could help lowering the dissolution rate of Portlandite in acid. Moreover it is likely that already used admixtures, like superplasticizers, play such a role in adsorbing at the $\text{Ca}(\text{OH})_2$ surface. The optimization of their conformation, with the aim of reducing k may lead to more durable materials.

7. Conclusion

We have introduced in this article a methodology, including holographic interferometry, that gives access to the space and time resolution of heterogeneous reactions. In the case of the study of the degradation of hydrated cement, it enables to clearly discriminate between the dissolution and precipitation stages of the deterioration. This technique has been used to measure the dissolution rate constant of hardened Portland cement in pure aqueous solutions of hydrochloric, nitric and sulfuric acids at pH 2. Unexpectedly, the three values have been found to compare well, about $1 \text{ mg/m}^2/\text{s}$. This is a direct demonstration that the degradation kinetics is mostly driven by precipitation. We have also measured the evolution of the reaction rate constant in nitric acid with the pH. Profiting from the resolving power of the technique, we have finally measured accurately the pH of the solution

close to the surface, where it has been found to be always strongly alkaline (between 11.5 and 12.5), whatever the bulk pH. Now that ordinary Portland cement has been studied, this technique may be used to test thoroughly the resistance to acid attack of other cementitious materials, known to offer better acid resistance, like calcium sulfoaluminate cements, or Portland cement containing silica fume.

Acknowledgements

We thank Maurizio Bellotto, Cédric Desroches, Fernand Chassagneux and Susan Stipp for fruitful discussions.

References

- [1] V. Zivica, A. Bajza, Acidic attack of cement based materials — a review. Part 1. Principle of acidic attack, *Construction and Building Materials* 15 (2001) 331.
- [2] V. Zivica, A. Bajza, Acidic attack of cement based materials — a review. Part 2. Factors of rate of acidic attack and protective measures, *Construction and Building Materials* 16 (2002) 215.
- [3] V. Zivica, Acidic attack of cement based materials — a review. Part 3. Research and test methods, *Construction and Building Materials* 18 (2004) 683.
- [4] F. Girardi, W. Vaona, R. DiMaggio, Resistance of different types of concretes to cyclic sulfuric acid and sodium sulfate attack, *Cement & Concrete Composites* 32 (2010) 595.
- [5] J. Monteny, N. DeBelie, L. Taerwe, Resistance of different types of concrete mixtures to sulfuric acid, *Materials and Structures* 36 (2003) 242.
- [6] D. Derry, M. Malati, J. Pullen, Effects of atmospheric acids on Portland cements, *Journal of Chemical Technology and Biotechnology* 76 (2001) 1049.
- [7] H. Okochi, H. Kameda, S. Hasegawa, N. Saito, K. Kubota, M. Igawa, Deterioration of concrete structures by acid deposition — an assessment of the role of rainwater on deterioration by laboratory and field exposure experiments using mortar specimens, *Atmospheric Environment* 34 (2000) 2937.

- 439 [8] S. Xie, L. Qi, D. Zhou, Investigation of the effects of acid rain on the
440 deterioration of cement concrete using accelerated tests established in
441 laboratory, *Atmospheric Environment* 38 (2004) 4457.
- 442 [9] M. Chen, K. Wang, L. Xie, Deterioration mechanism of cementitious
443 materials under acid rain attack, *Engineering Failure Analysis* 27 (2013)
444 272.
- 445 [10] S. Miyamoto, H. Minagawa, M. Hisada, Deterioration rate of hardened
446 cement caused by high concentrated mixed acid attack, *Construction*
447 *and Building Materials* 67 (2014) 47.
- 448 [11] R. Beddoe, H. Dörner, Modelling acid attack on concrete: Part i. The
449 essential mechanisms, *Cement and Concrete Research* 35 (2005) 2333.
- 450 [12] V. Zivica, Experimental principles in the research of chemical resistance
451 of cement based materials, *Construction and Building Materials* 12
452 (1998) 365.
- 453 [13] J. Colombani, J. Bert, Holographic interferometry for the study of
454 liquids, *J. Molec. Liquids* 134 (2007) 8.
- 455 [14] J. Colombani, J. Bert, Holographic interferometry study of the disso-
456 lution and diffusion of gypsum in water, *Geochim. Cosmochim. Acta*
457 71 (2007) 1913.
- 458 [15] E. Pachon-Rodriguez, J. Colombani, Pure dissolution kinetics of an-
459 hydrite and gypsum in inhibiting aqueous salt solutions, *AIChE J.* 59
460 (2012) 1622.
- 461 [16] J. Colombani, J. Bert, Holographic convection visualization during
462 thermotransport studies - Application to microgravity experiments,
463 *Meas. Sci. Technol.* 10 (1999) 886.
- 464 [17] C. Fischer, R. Arvidson, A. Luttge, How predictable are dissolution
465 rates of crystalline material?, *Geochim. Cosmochim. Acta* 98 (2012)
466 177.
- 467 [18] J. Colombani, Measurement of the pure dissolution rate constant of a
468 mineral in water, *Geochim. Cosmochim. Acta* 72 (2008) 5634.
- 469 [19] I. Pignatelli, A. Kumar, R. Alizadeh, Y. LePape, , M. Bauchy, G. Sant,
470 Does a dissolution-precipitation mechanism explain concrete creep in
471 moist environments?, *arXiv cond-mat* (2015) 1508.07082.